



NanoCrete 1345

Low dose, high range water reducing & slump retaining concrete admixture

Description	NanoCrete 1345 is a low dose, high range water reducing & slump retaining concrete admixture based on polycarboxylate which is flexible enough to use as an ASTM C 494 Type F & G.						
Primary applications	<ul style="list-style-type: none"> • High performance concrete • Self-compacting concrete • Precast concrete • Low water/cement ratio concrete • High early & ultimate strength applications 						
Advantages	<ul style="list-style-type: none"> • Improves finish ability • Improves workability • Reduces water requirement • Improves setting times • Superior slump retention • Increases early and late age strengths • Reduces permeability • Increases durability 						
Specifications	Complies with ASTM C-494 Type F & G.						
Packaging	210 Ltr. drums, 1000 Ltr. totes and bulk.						
Storage	Store in a dry and cool place below 35°C. Protect from direct sunlight.						
Shelf life	12 months if stored properly in original unopened packaging.						
Properties	<table> <tr> <td>Appearance:</td> <td>Brown/clear liquid</td> </tr> <tr> <td>Specific gravity:</td> <td>1.04 ± 0.01 at 20°C</td> </tr> <tr> <td>Chloride content:</td> <td>Nil to BS 5075.</td> </tr> </table>	Appearance:	Brown/clear liquid	Specific gravity:	1.04 ± 0.01 at 20°C	Chloride content:	Nil to BS 5075.
Appearance:	Brown/clear liquid						
Specific gravity:	1.04 ± 0.01 at 20°C						
Chloride content:	Nil to BS 5075.						
Instruction for use	<p>Dosage: 0.4-0.8 Ltr/100kg of cement. It is advisable to carry out trial mixes to establish the exact dosage rate required.</p> <p>Dispensing: NanoCrete 1345 should be added to gauging water prior to its addition to the dry mix concrete or separately to the freshly mixed concrete. When added separately to the freshly mixed concrete further mixing time of 2-3 minutes should be given.</p> <p>Placing: The standard rules of good concreting practice for production and placing must be observed when using NanoCrete 1345 concrete.</p> <p>Curing: Fresh concrete must be cured properly. Use NanoCure or wet hessian.</p> <p>Compatibility: NanoCrete 1345 is compatible with all types of cement.</p> <p>Effect of over dosing: When accidental overdosing occurs, the retardation of initial set air content and workability increases. During this period the concrete must be kept moist in order to prevent premature drying out.</p>						
Technical Support	Nano Vision offers technical support, services to consultant, end users and contractors. We also provide technical assistance on site.						
Cleaning & Disposal	All tools and equipment should be washed with water immediately after use. Do not dispose of into water or soil but according to local regulations.						
Precautions/Limitations	Do not allow freezing. Shake well before use.						
Health & safety	In case of contact with the skin, wash immediately with soap and water; In case of contact with the eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately, do not induce vomiting. Skin barrier cream, safety goggles and rubber gloves are recommended.						