



# NanoPlast P123

## Water reducing concrete admixture

<b>Description</b>	NanoPlast P123 is water reducing concrete admixture and is chloride free and based on a blend of specially selected lignosulphonate and synthetic polymers. It is supplied as a low viscosity brown solution which instantly disperses in water. NanoPlast P123 disperses the fine particles in the concrete mix, enabling the water content of the concrete to perform more effectively and improving the consistency of the concrete. This produces higher levels of workability for the same water content, allowing benefits such as water reduction and increased strengths to be taken.								
<b>Primary applications</b>	<ul style="list-style-type: none"> <li>• Flatwork concrete</li> <li>• Architectural concrete</li> <li>• General purpose ready mixed concrete</li> <li>• Precast concrete</li> </ul>								
<b>Advantages</b>	<ul style="list-style-type: none"> <li>• Improves workability</li> <li>• Reduces water requirement</li> <li>• Increases compressive strength</li> <li>• Reduces permeability</li> <li>• Improves finished appearance</li> <li>• Reduces shrinkage</li> <li>• Increases durability</li> <li>• Non-staining</li> </ul>								
<b>Specifications</b>	Complies with ASTM C-494, Type A.								
<b>Packaging</b>	210 Ltr. drums, 1000 Ltr. totes and bulk.								
<b>Storage</b>	Store in a dry and cool place below 35°C. Protect from direct sunlight.								
<b>Shelf life</b>	12 months if stored properly in original unopened packaging.								
<b>Properties</b>	<table> <tr> <td>Appearance:</td> <td>Brown liquid</td> </tr> <tr> <td>Specific gravity:</td> <td>1.15 ± 0.01 at 20°C</td> </tr> <tr> <td>Chloride content:</td> <td>Nil to BS 5075</td> </tr> <tr> <td>Air entrainment:</td> <td>Less than 2% at normal dosage.</td> </tr> </table>	Appearance:	Brown liquid	Specific gravity:	1.15 ± 0.01 at 20°C	Chloride content:	Nil to BS 5075	Air entrainment:	Less than 2% at normal dosage.
Appearance:	Brown liquid								
Specific gravity:	1.15 ± 0.01 at 20°C								
Chloride content:	Nil to BS 5075								
Air entrainment:	Less than 2% at normal dosage.								
<b>Instruction for use</b>	<p><b>Dosage:</b> 0.3-0.8 Ltr/ 100kg of cement. It is advisable to carry out trial mixes to establish the exact dosage rate required.</p> <p><b>Dispensing:</b> NanoPlast P123 should be added to gauging water prior to its addition to the dry mix concrete.</p> <p><b>Placing:</b> The standard rules of good concreting practice for production and placing must be observed when using NanoPlast P123 concrete.</p> <p><b>Curing:</b> Fresh concrete must be cured properly. Use NanoCure or wet hessian.</p> <p><b>Compatibility:</b> NanoPlast P123 is compatible with all types of cement.</p> <p><b>Effect of over dosing:</b> When accidental overdosing occurs, the retardation of initial set air content and workability increases. During this period the concrete must be kept moist in order to prevent premature drying out.</p>								
<b>Technical Support</b>	Nano Vision offers technical support, services to consultant, end users and contractors. We also provide technical assistance on site.								
<b>Cleaning &amp; Disposal</b>	All tools and equipment should be washed with water immediately after use. Do not dispose of into water or soil but according to local regulations.								
<b>Precautions/Limitations</b>	Do not allow freezing. Shake well before use.								
<b>Health &amp; safety</b>	In case of contact with the skin, wash immediately with soap and water, In case of contact with the eyes rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately, do not induce vomiting. Skin barrier cream, safety goggles and rubber gloves are recommended.								